



Stamp Top Grey

22.7 kg/50 lbs

Mix with 3.4 litres of water

NOTE:

It is important to not overwater Stamp Top. Excessive water will cause excessive colour bleed and result in a washed out colour.

DO NOT EXCEED 3.4LITRES OF WATER PER 22.7KG BAG OF STAMP TOP

MIXING PROCEDURE:

1. ADD WATER INTO A CLEAN MIXING BUCKET. HOLD BACK APROXIMATELY 250ML WATER FROM THE 3.4 LITERS TO ALLOW FOR SLIGHT VARIATIONS IN BAG WEIGHT.
2. SLOWLY ADD POWDER WHILE MIXING WITH A ½” DRILL AND MIXING PADDLE.
3. IF NECESSARY ADD THE REMAINING WATER TO ACHIEVE A CONSISTANT MIX FROM ONE BAG TO THE NEXT
4. MIX APROXIMATELY 1.5 MINUTES OR UNTIL AN HOMEGENOUS CONSISTANCY IS ACHIEVED.

DO NOT EXCEED 3.4 LITERES OF WATER PER 22.7KG BAG OF STAMP TOP

OTHER CONSIDERATIONS:

Place with gauge rake at desired thickness.

Let sit for 3 to 5 minutes.

Trowel once – DO NOT OVER TROWEL.

When Stamp Top has reached desired set apply release agent and begin stamping

When using Stamp Top use saw cuts or expansion joints as per normal redi-mix concrete.